

INFINIDENT

SOLUTIONS



Celtra® Duo

Highly esthetic all-ceramic restorations

CTE (25 – 500 °C)*

$11.8 \cdot 10^{-6} \cdot K^{-1}$

BENDING STRENGTH*

210 (polished) –
370 MPa (healing firing)



INDICATIONS

Crowns in the anterior and posterior regions to superstructures on implants through to veneers, inlays and onlays.

BENEFITS

- + Outstanding light optical properties
- + High edge stability and impressive strength
- + Quick and simple polishing in the laboratory
- + No additional crystallization firing necessary

REFERENCES

The restoration is customized using Celtra® Universal stains or Celtra® Universal liquids directly on the tooth-colored framework of the restoration. The products developed for Celtra® (e.g. Celtra® Cementation System) from Dentsply Sirona can be used for bonding Celtra® Duo. Please follow the manufacturer's instructions.

COMPOSITION*

ZrO ₂	10.1 %
SiO ₂	58.0 %
Li ₂ O	18.5 %
Other	13.4 %

* typical material characteristics.
The published information of the respective material manufacturer shall apply.